

## DRIVEWAY SUPER RUBBERIZED SEALER - CONTRACTOR GRADE 4 YEARS PROTECTION

A water-based and coal tar-based emulsion coating used to prevent cracks and deterioration of asphalt pavements caused by wear and tear, freezing, oil and gasoline spills, salt, sun and rain.

- Effectively seals the asphalt surface against water infiltration
- No unpleasant smell
- Easy and fast application

### PRODUCT PURPOSE

Application	Asphalt surface protection
Substrate	Asphalt


### PRODUCT CHARACTERISTICS

Installation Method	Scraper
---------------------	---------

### PACKAGING

Code	Containers	Indicative Covering	Quantity per Pallet
50000	17 l (4.5 US gal)	23 to 55 m <sup>2</sup> (250 to 600 ft <sup>2</sup> )	36

### INSTALLATION

Storage	12 months in the original container. Store in a cool, dry place, between 10 ° C (50 ° F) and 40 ° C (104 ° F). Keep away from frost.
Minimum Application Temperature	10 ° C (50 ° F)
Tools Required	 Scraper
Surface Preparation	The substrate must be clean and free of dust, grease or other contaminants.
Installation Prerequisite	Before hand repair the surface with RESISTOSEAL asphalt maintenance range of products.
Installation	<ol style="list-style-type: none"> <li>1. Mix thoroughly until smooth.</li> <li>2. Starting at the highest part of the area to be covered, pour DRIVEWAY SEALER in ribbon shapes over the asphalt.</li> <li>3. Apply the sealer with a scraper, taking care not to leave any excess product on the surface.</li> <li>4. Let the surface dry and then check for the hardening of the product before allowing normal traffic.</li> </ol>
Drying time	24 to 48 hours. 48 hours before parking a vehicle.
Cleaning	Clean damp tools with water. When dry, clean with solvents such as mineral spirits, paint thinner or xylene.
Tricks / Tips	For best results, do not apply the product in direct sunlight. In very hot weather, water the area first, before application, ensure that there is no standing water on the surface.
Recommendations/ Limitations	Avoid applying the product if there is a risk of rain, high humidity or frost within 24 hours of application. The asphalt surface must cure for a minimum of 15 days before the application of the ASPHALT PROTECTOR. Do not use on asphalt-based or gilsonite-based coatings.

