



N.I.S. ROOFING FELT ADHESIVE

TECHNICAL DATA SHEET
160126RCAN1E
(supersedes 110208RCAN1E)

DESCRIPTION

RESISTO SEAL NIS ROOFING FELT ADHESIVE is composed of selected bitumen, cellulose fibre, mineral fillers and fast-evaporating solvent. Used in cold process application to bond felt, NIS and bituminous papers.

APPLICATION

RESISTO SEAL NIS ROOFING FELT ADHESIVE is easily applied with a squeegee, brush or roller. Larger holes and cracks must first be filled with **RESISTO SEAL PLASTIC CEMENT** prior application. Stir well before use. Surfaces must be dry and free from oil, grease, dirt and loose materials prior application. Covers 1 to 2 L/m² (2.5 to 5 US gal/100 ft²) depending on surface porosity.

PROPERTIES

Properties	NIS ROOFING FELT ADHESIVE	
Colour	Black	
Specific gravity at 23 °C (73 °F)	1.06 kg/L	8.85 lbs/US gal
Service temperature range	-30 °C to 70 °C	-22 °F to 158 °F
Application temperature (product)	10 °C to 35 °C	50 °F to 95 °F
Application temperature (surface)	-5 °C to 35 °C	23 °F to 95 °F
Flow	None at these temperatures	
Cure time	Between 24 and 48 hours depending on temperature and quantity applied	
All values are nominal)		

PACKAGING

- 3.78 L (1 US gal) & 18.9 L (5 US gal) pails.
- Can be stored at temperatures below 0 °C (32 °F) without damage.
- Maximum storage temperature: 40 °C (104 °F).

CLEANING

Tools can be cleaned with petroleum solvents such as mineral spirits, xylene, etc.

RESTRICTIONS

Use of **RESISTO SEAL NIS ROOFING FELT ADHESIVE** is not recommended on metal or coal tar roofs. Do not use on slopes higher than 3/12.

PRECAUTIONS

RESISTO SEAL NIS ROOFING FELT ADHESIVE is a flammable product. Store in a cool, dry area. Use in a well ventilated area, away from any open flame. Harmful if inhaled, swallowed or when in contact with skin.

Consult the Material Safety Data Sheet for more details.

