

# SOPRA-XPS 25 CW



INSULATION

APPLICATIONS

WALLS

TECHNICAL DATA SHEET 180529SCANE

(supersedes -)

## DESCRIPTION

SOPRA-XPS 25 CW is a rigid thermal insulation board made of extruded polystyrene composed of closed cell foam. SOPRA-XPS 25 CW is mainly used as a thermal insulation for above grade SOPREMA wall systems.

SOPRA-XPS 25 CW insulation boards are scored squared every 400 mm (16 in) and 600 mm (24 in) so they can easily be cut when they need to fit perfectly between wall ties.

SOPRA-XPS 25 CW insulation boards are available with square edges on four sides.

SOPRA-XPS 25 CW does not have any CFC and HCFC - Zero ozone depletion potential.  
Minimum 20% recycled content pre-consumer (post industrial).

## INSTALLATION

### MECHANICALLY ATTACHED

Install insulation boards using fasteners and 50 mm (2") diameter washers.

When another layer of SOPRA-XPS 25 CW insulation is required, it should be installed with staggered joints on the first layer.

Maximum service temperature: 75 °C (167 °F).

## RESTRICTIONS

- SOPRA-XPS 25 CW is install where the applied loads do not exceed 20 psi.
- SOPRA-XPS 25 CW is a flammable product. To comply with the National Building Code, it must be used in combination with a thermal barrier.
- SOPRA-XPS 25 CW can not be used in a wall assembly with a combustible veneer.

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

## PACKAGING

Specifications	SOPRA-XPS 25 CW
Boards thickness*	40 mm (1.6 in) 50 mm (2 in) 61 mm (2.4 in) 75 mm (3 in) 100 mm (3.9 in)
Boards dimensions*	2400 mm x 1200 mm (7.9 ft x 3.9 ft)
Colour	Light orange

\* Other thicknesses and dimensions available upon request.  
(All values are nominal)



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

NOTE: All products manufactured by SOPREMA Inc. comply with the description and properties indicated in the technical data sheet that was current at the date of manufacture.

TDS\_SOPRA-XPS\_25\_CW.mdd

# SOPRA-XPS 25 CW



INSULATION

APPLICATIONS

WALLS

TECHNICAL DATA SHEET 180529SCANE

(supersedes -)

## PROPERTIES

SOPRA-XPS 25 CW meets the requirements of CAN/ULC S701.1 Type 3 (ASTM C578-14 Type IV).

Properties	Standards	SOPRA-XPS 25 CW
Thermal Resistance (RSI-Value [R Value] / 25.4 mm [1 in] @ 24 °C [75 °F])	ASTM C518	RSI- 0.88 (R – 5.0)
Water Vapour Permeance	ASTM E96 (Method A)	57 ng/Pa•s•m <sup>2</sup> (1.0 perm)
Dimensional Stability, max.	ASTM D2126	1.5 %
Min. Flexural Strength	ASTM C203	300 kPa (44 psi)
Water Absorption, % by volume, max.	ASTM D2842	0.7
Min. Compressive Strength	ASTM D1621	172 kPa (25 psi)
Limiting Oxygen Index	ASTM D2863	24 %

(All values are nominal)

## STORAGE AND HANDLING

SOPRA-XPS 25 CW thermal insulation boards are covered with a temporary waterproof packaging for handling the panels in the manufacturing plant and during transit.

SOPRA-XPS 25 CW thermal insulation boards must be stored on a flat substrate, protected from UV and sheltered from inclement weather. As they are flammable, they must be protected and kept away from flames and intense heat sources during transportation, handling, storage, and installation.



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

NOTE: All products manufactured by SOPREMA Inc. comply with the description and properties indicated in the technical data sheet that was current at the date of manufacture.

TDS\_SOPRA-XPS\_25\_CW.mdd